

# ASTRA-CRETE SLB

## product data sheet



### DESCRIPTION

ASTRA-CRETE SLB (self leveling broadcast) is a 100% solids aromatic cementitious urethane system with a quartz aggregate broadcast. This system is typically installed at a nominal thickness of 3 mm. This should be determined by service, cleaning temperatures, severity of traffic, point impact and loadings. A topcoat(s) of ASTRA epoxy, urethane or methyl methacrylate is used depending on performance requirements.

### BENEFITS

- VOC Compliant
- ADA Compliant
- Leed Credit Points Available
- Meets USDA, FDA and CFIA standards
- Hygienic - Does Not Harbor Bacteria
- High Chemical Resistance
- High Abrasion Resistance
- Self-Priming
- Wide Service Temperature Range,-40 to 100oC
- Can Be Installed With Moisture Levels Up To 6 Kgs/1,000 sf/24 hrs.
- Can Be Applied To 7-14 Day Old Concrete

### TYPICAL USES

ASTRA-CRETE SLB is designed to protect concrete, Polymer reinforced screeds, mild steel and water resistant plywood from chemical attack, corrosion, impact and thermal shock. It is also unaffected by freeze/thaw cycles.

- Aesthetic Considerations
- Wet Areas
- Commercial Kitchens and Restaurants
- Meat/Poultry and Dairy Processing
- Pharmaceutical Plants
- Processing Areas
- Exterior Applications

### SURFACE PREPARATION

This product requires preparation in order to perform as expected. Surface must be profiled, clean, dry, oil free and sound. Please refer to the “**Surface Preparation Guide**” for more information

### APPLICATION METHOD

ASTRA-CRETE SLB is applied to a properly prepared area at the required thickness using a “V” notched squeegee. The freshly placed material is then loop rolled into which the proper size quartz aggregate is broadcast to excess to achieve the desired profile. Allow a minimum of 8 hours for the Base Coat to cure before sweeping, sanding or vacuuming. Apply the desired pigmented coat(s) to achieve the required finish. ASTRA-CRETE CF and ASTRA-CRETE TF may be used to topcoat ASTRA-CRETE SLB systems. ASTRA-A-GLAZE NOVOLAC is also appropriate to use as a topcoat for ASTRA-CRETE SLB systems.

### LIMITATIONS

This product is best suited for application in temperatures between 10°C and 30°C. Substrate must be clean, sound and dry.

### PACKAGING

ASTRA-CRETE SLB is available in pre-measured kits and in Bulk Packing

### CHEMICAL RESISTANCE

ASTRA-CRETE SLB has excellent resistance to organic and inorganic acids, alkalis, fuel and hydraulic oils, as well as aromatic and aliphatic solvents.

### STORAGE CONDITIONS

ASTRA-CRETE SLB must be stored dry. Do not use partial bags of aggregate. Do not allow resins to freeze. Every ASTRA-CRETE product will be shipped with a lot number on the label. The first two digits indicate the year; the second two show the month, the third two will be the day. The shelf life is 6 months from the date on the label in the original unopened container.

### COLORS

Refer to the Color Selection Charts wide range of standard colors, special color matches may be available.

## ASTRA-CRETE SLB (TOPCOATS)

### TECHNICAL INFORMATION

	ASTRA-Crete KT	ASTRA-Crete CF	ASTRA-Crete TF
Cure Time @ 70°F	48 hrs	24 hrs	3-5days
Full			
Mix Ratio	3 part resin: 1 part hardener	3 Component Kit	3 Component Kit
Pot Life	15 minutes	25 minutes	15 minutes
Adhesion to Concrete	> 400 psi, concrete fails before loss of bond	> 400 psi, concrete fails before loss of bond	> 400 psi, concrete fails before loss of bond
Service Temperature	-40 to 100 C (live steam)	-40 to 100 C (live steam)	-40 to 100 C (live steam)
Available Color	Beige, Black, Charcoal, Concrete, Medium Grey, Slate Grey, Tile Red	Blue, Burnt Orange, Green, Charcoal, Concrete, Grey, Dark Grey, Red, Sandstone, Cream	Blue, Burnt Orange, Green, Charcoal, Concrete, Grey, Dark Grey, Red, Sandstone, Cream

Physical Property	Test Method	ASTRA-Crete KT	ASTRA-Crete CF	ASTRA-Crete TF
Hardness (Shore D)	ASTM D 2240	75-80 D	65 D	85 D
Compressive Strength	ASTM C 579	8,990 psi	7,800 psi	7,250 psi
Tensile Strength	ASTM D 638	2,175 psi	4,200 psi	750 psi
Impact Resistance	ASTM D1709	>160 in.-lb.	>160 in.-lb.	>160 in.-lb.
Flexural Strength	ASTM D 790	5,075 psi	1,000 psi	4,400 psi
Abrasion Resistance CS17 Wheel 1000 GM Load 1,000 Cycles	ASTM D 4060	35 mg loss	10 mg loss	40 mg loss
Coefficient of Friction Standard Slip-Resistant	ASTM D 2047	(Passes ADA commendations) 0.9	(Passes ADA recommendations) 0.9	(Passes ADA recommendations) 0.9
VOC Content		0 g/l	0 g/l	0 g/l

## DRAWINGS AND DETAILS

Standard CAD drawings and details are available for coves, drains, breaches, transitions, etc. Please refer to the Master **“Drawings and Details”** guide for actual drawings.

## GUIDE SPECIFICATIONS

This product is part of the family of ASTRA POLYMER systems. Please refer to the master **“Specifier’s Guide”** for complete three part guide specs.

## MOISTURE CONCERNS

Please refer to the Floor Evaluation Flow Chart in the Contractor’s Center of our website for a step-by-step process to determine the condition of the concrete.

## CLEANING

This product is considered to be a low maintenance flooring solution, however, certain textures and service environments require specific procedures. Please refer to the master **“Cleaning Guide”** for more information

## JOINT GUIDELINES

Refer to the Joint Guidelines for complete details on our website.

## CAUTION

Adequate cross ventilation should be provided. Read, understand and follow Material Safety Data Sheets and Application Instructions of this flooring system prior to use. Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed.

Before using any ASTRA. product, be sure the Material Safety Data Sheet is read and understood.

## WARRANTIES

Seller warrants that its goods, as described on the face hereof, are free from any defects in material or workmanship. Seller makes no other warranty, express or implied, and all implied warranties of merchantability and fitness for a particular purpose are hereby disclaimed. Seller shall not be liable for prospective profits or special indirect or consequential damages. Seller’s sole liability and buyer’s exclusive remedy for breach of any warranty as expressly limited, at seller’s option, to replacement at the original F.O.B. point or refund of purchase price. Seller shall not be responsible for any claim resulting from failure to utilize product in the manner in which it was intended and in accordance with instruction provided for use of product. Any claim for breach of warranty shall be deemed waived unless buyer shall give seller written notice of such claim within sixty (60) days after delivery and shall allow seller reasonable opportunity to investigate claim and inspect product.